


Absorption Coefficient of Fonic Acoustic Tiles



Frequency (Hz)	Fonic Acoustic Tiles
100	0.10
125	0.09
160	0.19
200	0.22
250	0.30
315	0.48
400	0.58
500	0.74
630	0.78
800	0.92
1,000	0.95
1,250	0.91
1,600	0.93
2,000	0.94
2,500	0.98
3,150	1.00
4,000	1.01
5,000	1.02
6,300	1.01
8,000	1.14
10,000	1.14
12,500	1.19
16,000	1.19
20,000	0.80
NRC	0.73